

System Description Sheet

Promenade and Roof Deck Waterproofing Surfacing System

1. PRODUCT DESCRIPTION

A. COMPOSITION

Weatherwear promenade and roof deck covering system is a multi-layered troweled applied waterproofing and wearing surface. It is designed for use as waterproof promenade decks and roof surfaces, such as sun decks, play roofs, observation decks, etc., which are subject to normal foot traffic, roof furniture and rubber-tired window washing rigs.

The material is applied in a series of troweled coatings, which form an elastic latex membrane with integral composition flashing and a flexible rubber-cement traffic surface. A unique "slip-sheet" divorces the system from the surface and permits it to "float" over normal building cracks and isolated element movement.

Weatherwear components consist of a combinations of dehydrated polymeric liquid rubber-latex in powder form and vulcanizers, as well as special pre-engineered aggregates.

The total thickness of the material is 3/16" (4,75mm) to 1/4" (6.35mm). It can be applied over plywood or concrete. After suitable preparation it may be installed over existing promenade surfaces of various types, such as quarry tile, flagstone, etc. Direct bond application may be substituted for the slip-sheet feature, contact Crossfield for recommendations. It is available in a wide range of colors.

Weatherwear is a fire retardant system, with a One Hour Fire-resistive Construction Rating and it is approved by the following agencies:

1. International Construction Conference (ICC), Class A Fire Retardant Roof Covering, Report No. 1338.
2. California State Fire Marshal, Listing No. 4175-291:1
3. City of Los Angeles Research Report No. 2360.

B. TYPICAL USES

Promenade roofs, condominium roofs, sun decks, play decks, office roofs where window washing equipment is used, etc.

C. ADVANTAGES AND LIMITATIONS

ADVANTAGES:

1. Monolithic, including integral flashing.
2. Slip-sheet permits "float" over cracks in substrate.
3. Installed only by Professional Factory Trained Dex-O-Tex Contractors.

LIMITATIONS:

1. Substrates must be dry when material is applied.
2. Not suitable for use when subjected to heavy steel wheeled loads.
3. Material subject to vapor damage upon water leakage underneath stemming from adjacent areas.
4. Moisture vapor transmission (MVT) in excess of 3.0 lbs/1000 sq/ft/per 24 hr period per ASTM F1869, may result in delamination, discoloration or improper curing. Use Dex-O-Tex Vapor-Lok 100 vapor control membrane over substrates, which have MVT emissions that exceed these limits. Consult with Crossfield prior to using Vapor-Lok 100 if moisture vapor transmission exceeds 15 lbs/1000 sq/ft/per 24 hr period per ASTM F1869.

2. TYPICAL PHYSICAL PROPERTIES at 75°F (24°C)

- A. Weight**..... 2.5 lbs. psf
- B. Accelerated Weathering** ASTM G23
(Atlas Twin-Arc Weatherometer: 120min. Cycle/102 mins. Dry at 145°F, 18 mins. Wet at 60° 2,000 hours) Under 5x Magnification, No cracking, blistering, chalking, crazing or color change.
Note: 2,000 hrs. as above is generally considered equivalent of 6 years natural weathering.
- C. Accelerated Aging** ASTM D756 No effect
Procedure D & E, 6 cycles (No chalking, crazing, cracking, blistering, delaminating, etc.)
- D. Freeze-Thaw** ASTM C67 No Breakage
(50 cycles)..... Weight loss >1%
- E. Water Resistance** MIL-D-1044 16 mg
- F. Chemical Resistance** ASTM D2299
- | | |
|----------------------------|--------------------------------------|
| Industrial Detergent (20%) | No color change or change in texture |
| Salt 20% solution | No color change or change in texture |
| Ammonia Solution (5%) | No color change or change in texture |
| Muriatic Acid 10% | No color change or change in texture |
| Chlorine (10%) | No color change or change in texture |
| Kerosene | No color change or change in texture |
| Turpentine | Slight softening of surface |
| Paint Thinner | Slight softening of surface |
- G. Percolation** ICBO Test
No moisture on underside, Max, drop in water column 0.10"
Complies ICBO Standard for this test.
- H. Water Absorption** MIL-D-3134 & ASTM D570..... 6.09%
(No warping, cracking, crazing under 5X magnification)
- I. Wind Uplift** Factory Mutual 1-52, Qualifying
Wind Velocity with a 3 Safety Factor – 131 m.p.h.
complies ICBO requirement.
- J. Fire Safety** ASTM E108, UL 790, NFPA 256
- | | |
|-----------------------------|---------|
| Intermittent Flame Exposure | Class A |
| Spread of Flame | Class A |
| Burning Brand | Class A |

3. OVERVIEW OF INSTALLATION STEPS

- A. On suitably pitched sub-surfaces apply Dex-O-Tex Slip Sheet.
- B. Apply Elastomeric rubber composition membrane with fabric reinforcement.
- C. Apply Dex-O-Tex integral flashing of similar construction as above.
- D. Apply two trowel coats of liquid rubber and aggregate composition traffic surfacing over entire deck. Sand to remove trowel ridges.
- E. Apply two grout-smoothing coats of rubber-cement composition to smooth surface.
- F. Roller apply two coats of surface dressing to achieve uniform surface.

System Description Sheet

Promenade and Roof Deck Waterproofing Surfacing System

For Substrate Preparation: See Weatherwear Architectural Information Sheet and its Detail Drawings for particulars. **Note:** Generally all Special Dex-O-Tex drains are available from major drain manufacturers. Consult Crossfield for current listings and plumbing roughing.

4. PRODUCT AVAILABILITY

Crossfield Products Corp. maintains offices and/or factories at all addresses listed below. Factory Trained Contractors are established in all major trading areas in the United States, Canada and various European, Latin American and Far East nations.

5. SKID RESISTANCE and CLEANABILITY

In general, the more aggressive the finished surface the greater the coefficient of friction and corresponding skid resistance, the more difficult to clean. The smoother the finished texture the easier the surface is to clean, but there is a loss of skid resistant properties.

6. CLEANING

Cleaning and disinfecting compounds and cleaning techniques can affect the color, gloss, texture and performance of the system. As a precautionary step, Crossfield recommends that the end-user test their cleaning and disinfecting compounds on a sample or on a small, out of the way finished area, utilizing the intended cleaning technique prior to cleaning the entire surface area. If no deleterious effects are observed, the procedure can be continued. If the cleaning and disinfecting compounds or cleaning techniques damage the system, modification of the cleaning material or techniques will be required. Contact your Representative for additional information.

7. SPECIFICATION ASSISTANCE

Consult Crossfield for specification assistance, detailing, etc. This consultation is highly recommended prior to specification.

8. TESTING

The technical data contained herein is the result of tests made in Crossfield's laboratories or in independent laboratories using small scale equipment, following generally accepted trade practices. Although this information is believed to be true and accurate, the use of different equipment for testing under dissimilar conditions or the testing of samples produced under dissimilar conditions may develop substantially different results.

LIMITED WARRANTY

NO WARRANTY SHALL BE EFFECTIVE UNTIL THE TERMS AND CONDITIONS OF SALE SET FORTH IN CROSSFIELD PRODUCTS CORP. INVOICE ARE MET.

Crossfield Products Corp. warrants to the purchaser of its products that such products are free from manufacturing defect. Crossfield does not warrant or guarantee the workmanship performed by any person or firm installing its products. Crossfield's obligation under this warranty is limited solely to the original purchaser and solely to the remedy of replacement in kind of any product which Crossfield sold which may prove defective in manufacture within one year from date of installation, provided said product was stored correctly and installed within the product's shelf life, by the original purchaser and which Crossfield examination shall disclose to Crossfield's satisfaction to be thus defective.

IN NO EVENT SHALL CROSSFIELD PRODUCTS CORP. BE LIABLE FOR ANY INCIDENTAL OR CONSEQUENTIAL DAMAGES. THIS WARRANTY IS EXPRESSLY GIVEN IN LIEU OF ALL OTHER WARRANTIES EXPRESSED OR IMPLIED, INCLUDING THE WARRANTIES OF MERCHANTABILITY AND FITNESS FOR USE AND ALL OTHER OBLIGATIONS OR LIABILITIES ON CROSSFIELD'S PART, AND WE NEITHER ASSUME NOR AUTHORIZE ANY PERSON OR PERSONS TO ASSUME FOR US ANY OTHER LIABILITY IN CONNECTION WITH THE SALE OF A CROSSFIELD PRODUCT. THIS WARRANTY SHALL NOT APPLY TO ANY OF CROSSFIELD'S PRODUCTS, WHICH HAVE BEEN SUBJECT TO ADULTERATION, ALTERATION, ABUSE OR MISUSE. CROSSFIELD PRODUCTS CORP. MAKES NO WARRANTY WHATSOEVER IN RESPECT TO ACCESSORIES, PARTS OR MATERIALS NOT SUPPLIED BY CROSSFIELD PRODUCTS CORP., WHICH ARE USED IN CONNECTION WITH ITS PRODUCTS. THE TERM "ORIGINAL PURCHASER" IN THIS WARRANTY MEANS THAT PERSON, CORPORATION OR ENTITY TO WHOM CROSSFIELD PRODUCTS CORP. SOLD ITS PRODUCT OR PRODUCTS. ANY ACTION TO ENFORCE ANY WARRANTY OR FOR BREACH OF CONTRACT OR ARISING OUT OF ANY CLAIM AGAINST CROSSFIELD PRODUCTS CORP. SHALL BE COMMENCED AND MAINTAINED ONLY IN A COURT OF COMPETENT JURISDICTION IN THE CONTINENTAL UNITED STATES OF AMERICA. THE PURCHASER ACCEPTS THESE TERMS AND CONDITIONS, AND HEREBY EXPRESSLY WAIVES ANY CLAIM TO ADDITIONAL DAMAGES.

CAUTION: ALWAYS KEEP OUT OF THE REACH OF CHILDREN.



DEX-O-TEX PRODUCT LINE Crossfield Products Corp.

West Coast Office
3000 E. Harcourt Street
Rancho Dominguez, CA
90221
310-886-9100
310-886-9119 fax

East Coast Office
140 Valley Road
Roselle Park, NJ
07204
908-245-2800
908-245-0659 fax

www.dexotex.com